# Celite<sup>®</sup> HYFLO SUPER-CEL

## **TECHNICAL DATA**

#### PRODUCT

Туре	Filter Aid
Description	Flux Calcined Diatomite

#### **TYPICAL PHYSICAL PROPERTIES**

Color	White to Off White
Appearance	Fine Powder
Density Wet, lbs/ft3 (g/cc)	19.5 (0.31)
Permeability (Darcy)	1.1
150 Mesh Screen Analysis, % retain	7.0
Median Particle Size, microns	30.6
pH, 10% in water	10.0
Specific Gravity	2.3
Moisture, as shipped (%)	< 1.0

#### **TYPICAL CHEMICAL ANALYSIS (%)**

Loss on Ignition (1000°C)	0.2
SiO <sub>2</sub>	89.6
Al <sub>2</sub> O <sub>3</sub>	4.0
Fe <sub>2</sub> O <sub>3</sub>	1.3
P <sub>2</sub> O <sub>5</sub>	0.2
CaO	0.5
MgO	0.6
$Na_2O + K_2O$	3.3

#### IMERYS

Sales Office 1732 North First Street, Suite 450 San Jose, CA 95112 Tel: 805-735-7791 info@worldminerals.com

#### Production Site

Lompoc, California, USA

### For important health and safety information, please refer to MSDS.

The physical properties of the products represent typical values obtained in accordance with IMERYS test methods and are subject to manufacturing variations. They are provided here as a general reference only, are subject to change without notice, and should not be relied on for any particular application. No guarantee is given or intended. For important health and safety information, please refer to MSDS.

Rev. Date: 10/03/13

